

ISOLAR SOLARLUX[®] Zweifach-Sonnenschutzgläser

Produktbezeichnung	Glasaufbau in mm	L _T	L _R (außen)	g-Wert	U _g in W/m ² K EN 673	b- Faktor	Selektivitäts- kennzahl
		in % (±2) nach EN 410					
ISOLAR SOLARLUX [®] A70 // 70.37	6: / 15-16 Ar / 4	70	13	37	1,0	0,47	1,9
ISOLAR SOLARLUX [®] A60 // 61.33	6: / 15-16 Ar / 4	61	14	33	1,0	0,42	1,8
ISOLAR SOLARLUX [®] A50 // 53.28	6: / 15-16 Ar / 4	53	18	28	1,0	0,35	1,9
ISOLAR SOLARLUX [®] A40 // 43.23	6: / 15-16 Ar / 4	43	22	23	1,0	0,29	1,8
ISOLAR SOLARLUX [®] D70* // 68.46	6: / 15-16 Ar /:4	68	21	46	1,1	0,58	1,5
ISOLAR SOLARLUX [®] D60* // 58.40	6: / 15-16 Ar /:4	58	28	40	1,1	0,50	1,5
ISOLAR SOLARLUX [®] D50* // 50.33	6: / 15-16 Ar /:4	50	30	33	1,1	0,41	1,5
ISOLAR SOLARLUX [®] D40* // 40.28	6: / 15-16 Ar /:4	40	36	28	1,1	0,35	1,4
ISOLAR SOLARLUX [®] E70 // 70.39	6: / 15-16 Ar / 4	70	12	39	1,0	0,49	1,8
ISOLAR SOLARLUX [®] neutral // 61.34	6: / 15-16 Ar / 4	61	13	34	1,0	0,43	1,79
ISOLAR SOLARLUX [®] silber-light // 57.47	6: / 15-16 Ar /:4	57	35	47	1,1	0,59	1,21
ISOLAR SOLARLUX [®] silber // 40.21	6: / 15-16 Ar / 4	40	33	21	1,0	0,27	1,9
ISOLAR SOLARLUX [®] silber-blau // 37.27	6: / 15-16 Ar /:4	37	18	27	1,1	0,34	1,37

../2

ISOLAR SOLARLUX® Dreifach-Sonnenschutzgläser

Produktbezeichnung	Glasaufbau in mm	L _T	L _R (außen)	g-Wert	U _g in W/m ² K EN 673	b- Faktor	Selektivitäts- kennzahl
		in % (±2) nach EN 410					
ISOLAR SOLARLUX® A70 /// 63.34	6: / 14 Ar / 4 / 14 Ar / :4	63	15	34	0,6	0,43	1,8
ISOLAR SOLARLUX® A60 /// 56.31	6: / 14 Ar / 4 / 14 Ar / :4	56	16	31	0,6	0,38	1,8
ISOLAR SOLARLUX® A50 /// 48.26	6: / 14 Ar / 4 / 14 Ar / :4	48	19	26	0,6	0,32	1,9
ISOLAR SOLARLUX® A40 /// 39.21	6: / 14 Ar / 4 / 14 Ar / :4	39	23	21	0,6	0,26	1,8
ISOLAR SOLARLUX® D70* /// 62.41	6: / 14 Ar / 4 / 14 Ar / :4	62	23	41	0,6	0,51	1,5
ISOLAR SOLARLUX® D60* /// 53.35	6: / 14 Ar / 4 / 14 Ar / :4	53	29	35	0,6	0,44	1,5
ISOLAR SOLARLUX® D50* /// 45.29	6: / 14 Ar / 4 / 14 Ar / :4	45	31	29	0,6	0,36	1,6
ISOLAR SOLARLUX® D40* /// 36.24	6: / 14 Ar / 4 / 14 Ar / :4	36	36	24	0,6	0,30	1,5
ISOLAR SOLARLUX® E70 /// 64.36	6: / 14 Ar / 4 / 14 Ar / :4	64	14	36	0,6	0,45	1,8
ISOLAR SOLARLUX® neutral /// 56.31	6: / 14 Ar / 4 / 14 Ar / :4	56	16	31	0,6	0,39	1,8
ISOLAR SOLARLUX® silber-light /// 53.40	6 : / 14 Ar / :4 / 14 Ar / :4	53	37	40	0,6	0,5	1,33
ISOLAR SOLARLUX® silber /// 36.19	6: / 14 Ar / 4 / 14 Ar / :4	36	33	19	0,6	0,24	1,9
ISOLAR SOLARLUX® silber-blau /// 34.23	6: / 14 Ar / :4 / 14 Ar / :4	34	18	23	0,6	0,29	1,48

* oHt = optional heat treatable

Stand: 02-2018